### **Technical datasheet EN-011**

#### **MARCH 2022**

# **Epifanes PP Varnish Extra**

## Two component build up varnish with UV filter













#### PRODUCT DESCRIPTION

Epifanes PP Varnish extra is a quick drying high gloss varnish. The good scratch resistance makes it a very suitable varnish in a new system. It gives a good protection against water, household chemicals and alcohol. The varnish can be applied on every type of marine wood including teak and it has a great elasticity. It is therefore suitable for masts and other moving wooden parts of the boat.

**Field of use:** The professional, fast drying base varnish can be applied on every wooden surface above the waterline. Due to the limited UV protection, this product will show some loss of gloss and yellowing when exposed to UV. For exterior use, it is recommended to finish the system with either at least 3 coats Epifanes Poly-urethane Gloss/Satin, Epifanes PU Speedcoat or Epifanes Clear Varnish.

#### PRODUCT INFORMATION

**Type** Chemical drying

Base Polyurethane/Alkyd resin and isocyanate

Gloss High gloss
Colour Transparent
Density at 68°F. 1,034 g/cm³

Viscosity 40 seconds IS0-cup 4 mm

Solids Contents 50 ± 2 vol. %

VOC-level 538 g/l

Packing 1000ml. Component A + 1000ml. Component B = 2000ml.

5000ml. Component A + 5000ml. Component B. = 10 ltr.

**Shelf life** In closed, unopened container stored in a dry room at temperatures between 41-86°F

Component A 3 years after production date Component B 1 year after production date

**Rec. Film thickness** 2-2.5 mil wet = 1-1.5 mil dry

Induction time 68°F. 5-10 minutes

Thinner brush Epifanes PP Varnish Extra Thinner (Fast) / Epifanes Poly-urethane Brush Thinner (Slow)

Thinner spray Epifanes PP Varnish Extra Thinner

Thinning in general Thinning ratio depends on product temperature and working area. Avoid overthinning.

Drying times	59°F.	68°F.	77°F.
Dust dry	1 hour	30 minutes	25 minutes
Recoatable	3-4 hours	2-3 hours	2 hours
Sandable	30 hours	24 hours	20 hours
Potlife after mixing	2 hours	1.5 hours	1 hour

The above mentioned drying times are indicative at 65% RAH and 1 mil dry film thickness. Drying also depends on the amount of ventilation and applied wet film thickness. Higher wet film thickness and/or lpoor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness. Allow each varnish coat sufficient time to dry.

Substrate Bare wood: degreased and sanded 180G. Thin the first coat with 25% for teak. All other

woods first coat 30-40% thinned.

W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 – 360366 info@epifanes.nl www.epifanes.nl



1

#### Technical datasheet EN-011

#### **MARCH 2022**

# **Epifanes PP Varnish Extra**

## Two component build up varnish with UV filter

#### **APPLICATION**

**Conditions during application Temperature** Relative air humidity minimal 50°F. - maximal 86°F. minimal 50% - maximal 75%

Best results are achieved by using a longhaired soft brush or spray gun. Evenly distribute the varnish on the surface and tip off along the wood grain. Avoid retipping. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or much wind. A rapid loss of solvents will occur under these conditions and will decrease the flowing ability. Avoid large differences in temperature of the product, surface to be varnished and working area. In case the product "pulls" and is difficult to apply, 10% thinner may be added. To retrieve the original colour of the wood, up to 10% Epifanes Mahogany Stain or Epifanes Teak Stain may be added to the varnish. After drying, lightly sand the surface with 320G or use Scotch Brite. Always sand by hand along the wood

Guidelines for air spray application:

Thinning volume	Nozzle RP	Pressure	Visco DIN-cup 4 mm
10-25%	1.2 mm - 1.6 mm	30-37 psi	18-20 sec.

	Step 1	Step 2
Product	EPIFANES PP Varnish extra	EPIFANES PP Varnish extra
Numb. of coats		At least 3, but the more, the better
Thinner	EPIFANES Thinner for PP Varnish	Epifanes Thinner for PP Varnish
Thinning ratio	25%	0-10%
Drying time 68°F.	2-3 hours	2-3 hours
Sanding grit	Dry 220G	No sanding between coats within 48 hours. After 48 hours always sand with 320G
Remarks	First penetrating varnish coat. For full varnish penetration into the wood fibers, apply first coat heavily thinned.	PP Varnish Extra may be thinned with Epifanes PU Brushthinner. This slow evaporating thinner will allow the PP Varnish Extra to flow better.

with either at least 3 coats Epifanes Poly-urethane Gloss/Satin, Epifanes PU Speedcoat or Epifanes Clear Varnish. These products contain high end UV filters protecting

the system against loss of gloss.

Theoretical coverage Practicle coverage

150ft² per liter @ 1 mil dry filmthickness

Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatbility with other **Epifanes varnishes** 

Epifanes Clear Varnish 1-C High gloss alternative **Epifanes Woodfinish Gloss** 1-C High gloss alternative

Epifanes Woodfinish Matte 1-C Matt finish for interior / exterior use

**Epifanes Rubbed Effect Varnish** 1-C Satin finish for interior use Epifanes Poly-urethane Clear Satin 2-C Satin finish with UV Filter

Epifanes PU Speedcoat Clear Gloss/Satin 2-C Spray finish for interior / exterior use with UV filter

Safety

The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

Allthough the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unitended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties.

THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss ) shall be available to buyer.

W. Heeren & Zoon BV W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 – 360366 info@epifanes.nl www.epifanes.nl

